

N-SF8
689313.290

$n_d = 1,68894$	$v_d = 31,31$	$n_F - n_C = 0,022005$
$n_e = 1,69413$	$v_e = 31,06$	$n_F' - n_C' = 0,022346$

Brechzahlen		
	λ [nm]	
$n_{2325,4}$	2325,4	1,64448
$n_{1970,1}$	1970,1	1,65060
$n_{1529,6}$	1529,6	1,65753
$n_{1060,0}$	1060,0	1,66600
n_t	1014,0	1,66711
n_s	852,1	1,67203
n_r	706,5	1,67904
n_C	656,3	1,68254
$n_{C'}$	643,8	1,68354
$n_{632,8}$	632,8	1,68448
n_D	589,3	1,68874
n_d	587,6	1,68894
n_e	546,1	1,69413
n_F	486,1	1,70455
$n_{F'}$	480,0	1,70589
n_g	435,8	1,71775
n_h	404,7	1,72948
n_i	365,0	
$n_{334,1}$	334,1	
$n_{312,6}$	312,6	
$n_{296,7}$	296,7	
$n_{280,4}$	280,4	
$n_{248,3}$	248,3	

Konstanten der Dispersionsformel	
B_1	1,55075812
B_2	0,209816918
B_3	1,462054910
C_1	0,01143383440
C_2	0,0582725652
C_3	133,2416500

Konstanten der Formel für dn/dT	
D_0	-1,94E-06
D_1	9,70E-09
D_2	-2,34E-11
E_0	8,32E-07
E_1	1,15E-09
λ_{TK} [μ m]	0,276

Temperaturkoeffizienten der Lichtbrechung						
[°C]	$\Delta n_{rel}/\Delta T$ [$10^{-6}/K$]			$\Delta n_{abs}/\Delta T$ [$10^{-6}/K$]		
	1060,0	e	g	1060,0	e	g
-40/-20	1,0	2,4	4,2	-1,3	0,1	1,8
+20/+40	0,9	2,6	4,8	-0,5	1,2	3,3
+60/+80	1,0	2,9	5,3	-0,1	1,7	4,1

Reintransmissionsgrad τ_i		
λ [nm]	τ_i [10mm]	τ_i [25mm]
2500	0,750	0,480
2325	0,820	0,600
1970	0,950	0,870
1530	0,988	0,970
1060	0,997	0,993
700	0,995	0,987
660	0,993	0,983
620	0,993	0,983
580	0,994	0,986
546	0,993	0,983
500	0,985	0,963
460	0,976	0,940
436	0,965	0,910
420	0,950	0,880
405	0,920	0,810
400	0,900	0,770
390	0,830	0,630
380	0,670	0,370
370	0,350	0,070
365	0,160	
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

Farbcode	
$\lambda_{80} / \lambda_{5}$	41/36

Bemerkungen	
(*= λ_{70}/λ_5)	

Relative Teildispersionen	
$P_{s,t}$	0,2236
$P_{C,s}$	0,4778
$P_{d,C}$	0,2905
$P_{e,d}$	0,2362
$P_{g,F}$	0,5999
$P_{i,h}$	
$P'_{s,t}$	0,2202
$P'_{C,s}$	0,5152
$P'_{d,C'}$	0,2413
$P'_{e,d}$	0,2326
$P'_{g,F'}$	0,5308
$P'_{i,h}$	

Abweichung relativer Teildispersionen ΔP von der "Normalgeraden"	
$\Delta P_{C,t}$	0,0080
$\Delta P_{C,s}$	0,0019
$\Delta P_{F,e}$	0,0014
$\Delta P_{g,F}$	0,0087
$\Delta P_{i,g}$	

Sonstige Eigenschaften	
$\alpha_{-30/+70^\circ C}$ [$10^{-6}/K$]	8,6
$\alpha_{+20/+300^\circ C}$ [$10^{-6}/K$]	9,9
T_g [°C]	567
T_{10}^{13} [°C]	564
$T_{10}^{7,6}$ [°C]	678
c_p [J/(g·K)]	0,770
λ [W/(m·K)]	1,030
ρ [g/cm ³]	2,90
E [10^3 N/mm ²]	88
μ	0,245
K [10^{-6} mm ² /N]	2,95
$HK_{0,1/20}$	600
HG	4
CR	1
FR	0
SR	1
AR	1
PR	1
SR-J	1
WR-J	1